

160 MOLY SLIDE & WAY LUBE ISO 32 to 220

Moly Slide & Way Lube is premium quality anti-wear lubricant that is specially formulated to meet the lubrication requirements for accuracy and parts finish of machine tool horizontal, vertical and inclined slide ways, tables, and feed mechanisms. Moly Slide & Way Lube is designed for use on a wide range of materials used for machine tool slideway surfaces including cast iron and synthetic materials. Moly Slide & Way Lube is especially recommended for use in machine tool applications, where exposure to water soluble or water-mixable cutting fluids exists. The use of Moly Slide & Way Lube will reduce stick-slip and chatter even under thin film boundary lubrication conditions thus allowing for smooth, uniform motion at design travel speeds.

Moly Slide & Way Lube is blended from the finest high viscosity index solvent refined hydro-finished 100% pure paraffin base stocks available. These high viscosity index 100% pure paraffin base stocks allow Moly Slide & Way Lube the ability to possess excellent thermal, oxidation and chemical stability.

Blended into these high viscosity index paraffin base stocks is a unique patented additive package that is designed to provide an extra margin of protection by satisfying the stringent demands of the slide ways and other lubricated components of the machine tool, while providing exceptional anti-wear and load carrying performance, outstanding thermal and oxidation stability, rust and corrosion protection and rapid water separation. This patented additive technology provides the Moly Slide & Way Lube with the following performance features and benefits:

- Low frictional properties to eliminate stick-slip and chatter of slides and ways thus allowing for more accurate positioning, improved finished surface quality and improved dimensional accuracy of workpieces.
- Excellent anti-wear and load carrying capacity that reduces wear and increases smoothness of sliding action.
- Excellent adhesiveness and metal wetting capabilities that resists squeeze-out, wash-off by metalworking fluids and removal of the Moly Slide & Way Lube from critical surfaces.
- Excellent demulsibility characteristics. Moly Slide & Way Lube separates rapidly and completely from water and water-extendable or water soluble coolants thereby reducing the potential for the negative effects of cross-contamination that can lead to the loss of performance and service life of both the lubricant and the coolant.
- Excellent hydrolytic stability.
- Enhanced compatibility with existing fluids.
- Excellent rust and corrosion protection that extends component life and protects multi-metallurgy components.
- Excellent filterability in both wet and dry conditions.
- Excellent protection against the formation and build-up of varnish and sludge deposits.
- Enhanced thermal and oxidation stability.
- Excellent machine cleanliness.
- Excellent anti-foaming and air release properties
- Excellent fluid quality reserve to maintain its performance features even under severe service conditions and extended drain intervals.
- Enhanced fluid service life.
- Enhanced seal life.
- Reduced system maintenance.

Continued on next page

The trend by machine tool OEMs is to employ higher speeds, higher pressures, increased feed and cycling times and increased power output, while minimizing the oil reservoir size in order to make the systems more compact. These trends coupled with higher oil flow rates relative to the amount of the way lube present in the system has resulted in higher operating temperatures, which increases the rate of oxidation and thermal degradation and results in the potential formation of varnish and sludge deposits.

VarnishShield™ is a patented way lube fluid technology that is designed to prevent the formation and the build-up of varnish deposits, while providing exceptional anti-wear performance, outstanding thermal and oxidation stability, rust and corrosion protection and rapid water separation. The **VarnishShield™** additive system provides Moly Slide & Way Lube with a high degree of thermal and oxidative stability thus minimizing the formation of sludge and varnish. If any varnish particles do form, the dispersancy of the **VarnishShield™** additive will keep these particles suspended and prevent them from depositing on critical internal components. This helps eliminate the replacement of critical components and the costs associated with these activities.

The trend by machine tool OEMs to employ higher speeds, higher pressures, increased feed and cycling times and increased power output, while minimizing the oil reservoir size, and the fact that the equipment may be operating beyond its design capacity, can result in thin film lubrication conditions. These thin film lubrication conditions can cause increased wear conditions which may result in a loss in system efficiency and also in increased stick-slip and chatter of the slide and ways that can lead to poor finish and quality of parts and loss of production.

Moly Slide & Way Lube also contains Micron Moly®, a liquid soluble type of moly that plates itself to sliding, rolling and rubbing metal surfaces of the slides and ways. This plating action forms a long lasting solid lubricant film on sliding and rubbing surfaces that will withstand pressures up to 500,000 pounds per square inch. Micron Moly® not only produces a smooth finish surface, but also reduces friction between the moving parts which results in less heat being generated, lower operating temperatures, and a reduction in downtime.

Moly Slide & Way Lube also contains adhesive-cohesive additives that allow the product to strongly adhere to the slides and ways.

Moly Slide and Way Lube can also be used in the lubrication of ballscrews, linear guides, headstocks, translating screws, and lightly loaded gear box applications.

Moly Slide & Way Lube meets and exceeds the requirements of Cincinnati Machine P-47 (ISO 68) and P-50 (ISO 220), S.I.P. Manufacturing ISO 19378/ISO 6743-13 GA and GB and DIN CGLP.

Continued on next page

TD-160 (REV 11/2017)

TYPICAL PROPERTIES

ISO Grade	32	46	68	100	150	220
AGMA Grade	----	1	2	3	4	5
Specific Gravity 60°F	.8626	.8625	0.8669	0.8862	.8866	0.8623
Viscosity SUS 100°F (ASTM D-445)	155-207	123-250	336-361	479-632	757-811	1036-1077
Viscosity cSt 40°C (ASTM D-445)	28.8-35.2	41.4-50.6	65-70	92-121	135-165	196-205
Viscosity cSt 100°C (ASTM D-445)	5.0-6.0	6.2-7.5	8.5-9.5	10.5-13.0	13.5-16.0	17.0-19.0
Viscosity Index (ASTM D-2270)	109	112	100	100	98	105
Flash Point °F/°C (ASTM D-92)	410°/210°	410°/210°	430°/221°	450°/232°	470°/243°	485°/252°
Pour Point °F/°C (ASTM D-97)	-25°/-32°	-10°/-23°	0°/-18°	10°/-12°	20°/-7°	20°/-7°
Rust Test (ASTM D-665)						
Procedure A (Distilled Water)	Pass	Pass	Pass	Pass	Pass	Pass
Procedure B (Salt Water)	Pass	Pass	Pass	Pass	Pass	Pass
Copper Strip Corrosion Test 3 hours (ASTM D-130)	1a	1a	1a	1a	1a	1a
Four Ball Wear Test (ASTM D-4172) (1hr./40kg/130°F)						
Mean Scar Diameter (mm)	0.4	0.4	0.4	0.4	0.35	0.35
Four Ball Wear Test (ASTM D-4172) (1hr./20kg/130°F)						
Mean Scar Diameter (mm)	0.27	0.27	0.27	0.27	0.33	0.33
Four Ball EP Test (ASTM D-2783), Weld Point, kg	160	160	160	160	200	200
Falex Continuous Load (ASTM D-3233), Failure Load lbs.	1250	1250	1250	1500	1500	1500
Conradson Carbon Residue (ASTM D-189) % Residue	0.3	0.3	0.3	0.3	0.3	0.3
Foam Test (ASTM D-892) Sequence I	0/0	0/0	0/0	0/0	0/0	0/0
Sequence II	0/0	0/0	0/0	0/0	0/0	0/0
Sequence III	0/0	0/0	0/0	0/0	0/0	0/0
FZG Gear Test (ASTM D-5182), Load Stage Pass	12 th	12 th	12 th	12 th	12 th	12 th
Air Release (ASTM D-3427), Time (Minutes @ 122°F)	6.2	6.2	6.2	6.2	6.2	6.2
Hydrolytic Stability (ASTM D-2619), Copper Wt. Loss mg/cm ²	0.0556	0.0566	0.0566	0.0566	0.0566	0.0566
Acidity of Water mg/KOH	0	0	0	0	0	0
Demulsibility Test (ASTM D-1401), O-W-E	40-40-0	40-40-0	40-40-0	40-40-0	40-40-0	40-40-0
Time, min	15	15	15	15	15	15
Oxidation Stability Test (ASTM D-943), Hours to TAN of 2	3500+	3500+	3500+	3500+	3500+	3500+
Sludge Tendencies (ASTM D-4310), TAN after 1000 hours	0.34	0.34	0.34	0.34	0.34	0.34
Insoluble Sludge, Total Copper, mg.	39.4	39.4	39.4	39.4	39.4	39.4
Total Copper, mg	0.1	0.1	0.1	0.1	0.1	0.1
Thermal Stability Test (ASTM D-2070), 168 hr/135°C, (Copper/Steel Catalyst)						
Sludge (mg/100ml)	1.8	1.8	1.8	1.8	1.8	1.8
Copper weight loss,mg/100ml	0.2	0.2	0.2	0.2	0.2	0.2
Condition of Copper rod	3	3	3	3	3	3
Aniline Point °F/°C (ASTM D-611)	220°/104°	228°/109°	228°/109°	233°/112°	240°/116°	252°/122°
Total Acid Number (ASTM D-664)	0.91	0.91	0.91	0.91	0.91	0.91